Product Specification



RESICHEM 554 RB MEMBRANE

Resichem 554 RB Membrane is a single component solvent based rubberised acrylic waterproof coating. The product has been specifically designed as a waterproof coating for roof surfaces in cold climates.

Typical applications

The product is supplied ready to use and is ideal for water proofing roofs, gutters, tank bases and fibreglass structures

Characteristics

Appearance Single Component:

Thixotropic acrylic emulsion

Mixing Ratio

Single Component

Density 1.35

Solids content

50%

Sag Resistance

Nil at 750 microns

Coverage

Brush or roller applications: The material can be applied in a range of thicknesses dependent on the application.

300 microns WFT 3.33m² per ltr 500 microns WFT 2m² per ltr 750 microns WFT 1.33m² per ltr

Cure Times

The applied material should be allowed to harden for the times indicated below before being subjected to the conditions indicated:

Shower Proof

5°C	45 minutes
10°C	30 minutes
20°C	15 minutes

Touch Dry

5°C	6 hours
10°C	4 hours
20°C	2 hours

Minimum overcoating time

5°C	24 hours	
10°C	16 hours	
20°C	8 hours	

Maximum overcoating time Indefinite

Storage life

5 years if unopened and stored in normal dry conditions (15-30°C)

Mechanical Properties Elongation

Tested to ASTM D412 140%

Tensile Strength

Tested to ASTM D412 32kg/cm² (460psi)

Direct Pull Adhesion Tested to ASTM D4541 28kg/cm² (400psi)

Water

Vapour

Permeability Tested to ASTM D1653 2 x 10⁴ perm.cm

Heat Resistance Resistant to dry heat up to 100°C dependent on load.

Quality

All Resimac Products are supplied under the scope of the company's fully documented quality system.

Warranty

Resimac warrants that the performance of the product supplied will conform to the typical descriptions quoted within this specification provided material is stored correctly and used according to the procedures detailed in the Technical Data Sheet for the material.

Health and safety

Please ensure good practice is observed at all times during the mixing and application of this product. Protective gloves and other recommended personal protective equipment must be worn during the mixing and application of this product. Before mixing and applying the material please ensure you have read and fully understood the detailed Material Safety Data Sheet

Legal Notice: The data contained within this Product Specification is furnished for information only and is believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the customer to determine the products suitability for use. Resimac accepts no liability arising out of the use of this information or the product described herein.

Resimac Ltd, Unit B, Park Barn Estate, Station Road, Topcliffe, Thirsk, YO7 3SE, United Kingdom Tel: +44 1845 577498 Email: info@resimac.co.uk Web: www.resimacsolutions.com