

POLYUREA RAYSTON



Pure polyurea membrane for waterproofing in spray applications.

DESCRIPTION

Polyurea Rayston fast is a 2-component polyurea system for elastic membrane application with crack-bridging capability. It is an extra fast-curing system that can only be applied by hot mechanical spraying equipment. Polyurea Rayston can be combined with different geotextiles to obtain on site applied, seamless liners.



APPLICATIONS

Waterproofing of concrete structures. Roof waterproofing. Sewage and wastewater treatment structures. On-site applied liners, totally seamless, for secondary containment applications, ponds, landfills, tunnels, canals, dam repairing. Polyurea Rayston can be completed with an aliphatic polyurethane topcoat to ensure UV protection.



PROPERTIES

- Crack-bridging capability. Highly elastic membrane.
- Very fast curing, using two-component spraying equipment.
- It can be pigmented.



CERTIFICATIONS

CE marking EN 1504-2: 0370-CPR-2247, • **ETA (ETAG005):** European Technical Assessment document N° 16/0148.



BBA: British Board of Agreement Certificate 18/5582



Applus (Independent laboratory):

- Drinking water certification (Migration test). 928/09/8505
- Contact with alcoholic beverages. Simulation C as per regulation EU 10/2011 (EN 1186): pass. Certificate 928/11/4106 M1
- Low-temperature foldability: 11/2855-1313
- Mechanical properties: 11/2855-1314
- Dynamic and Static indentation test according to EOTA. 11/2855-1315
- Contact with fuel products (UNE 48307:2011) Exp 13/6620-457
- External fire resistance EN 13501-5:2005+A1 :2010

Water Regulations Advisory Scheme LTD. (WRAS) Material Approval (United Kingdom, contact with water intended for human consumption). Approval number 1709541

AITEX (Independent laboratory):

- Mechanical properties EN ISO 527-1/3.
- Static indentation/GBR UNE-EN-ISO 12236:2007.
- Tear, according to UNE-EN ISO 34-1:2011

TECHNICAL DATA

INFORMATION ON THE PRODUCT BEFORE APPLICATION

| | Component A | Component B |
|-----------------------------|-----------------|--------------------------------|
| Chemical description | Polyamine | Aromatic isocyanate prepolymer |
| Physical state | Liquid | Liquid |
| Packaging | Metal container | Metal container |

Note: Pigment is delivered

| | | |
|--|--------------------------|---------|
| in a third container. See Pigment Spray data sheet for specific details. | 185 kg | 211 kg |
| | 23.1 kg | 26.3 kg |
| Non-volatile content (%) | 100% | 100% |
| Flash point | >100°C | >100°C |
| Colour | Yellow (without pigment) | Yellow |

| Density | Temp (°C) | Density (g/cm3) | Temp (°C) | Density (g/cm3) |
|---------|-----------|-----------------|-----------|-----------------|
| | 20 | 1,02 | 20 | 1,12 |
| | 60 | 1,01 | 60 | 1,10 |

Viscosity

| Approximate values Brookfield | Temp (°C) | Viscosity (mPa.s) | Temp (°C) | Viscosity (mPa.s) |
|-------------------------------|-----------|-------------------|-----------|-------------------|
| | 20 | 600 | 20 | 2000 |
| | 30 | 200 | 30 | 1000 |
| | 50 | 60 | 50 | 400 |
| | 70 | 40 | 70 | 150 |

A/B mixing ratio A=100, B=117 by weight
A=100, B=100 by volume

Density and viscosity of the AB mixture Fast polymerization (see pot life data)

Colour Dark yellow, but component A is pigmented by addition of pigment paste (Pigment Spray) delivered with each kit of Polyurea Rayston.

Curing performance Gel time mixture A+B (20 g)
4 s at 25°C
3 s at 60°C
Tack free time
30 s at 70°C

Storage Keep between 10°C and 30°C.

Use before 12 months after manufacturing date.

INFORMATION ON THE FINAL PRODUCT

| | |
|-------------------------|--|
| Final state | Elastomeric solid membrane |
| Colour | Available Pigment Spray pastes are blue RAL 5015, gray RAL 7011. Tile red, beige RAL 1001. Other pastes are available under request. |
| Gloss (60°) | 80-85 |
| Hardness (shore) | 87A 35D |

Mechanical properties

| Elongation (%) | Tensile strength (mPa) |
|----------------|------------------------|
| 50 | 9.8 |
| 100 | 11 |
| 200 | 13 |
| 300 | 15.5 |
| 324 | 16.2 |

Maximum elongation: 324%
Tensile strength: 16,2 MPa
(UNE EN ISO 527-1/3)
Tear strength 61.8 N/mm
(UNE EN ISO 527-1/3)

Chemical resistance Immersion test.
(0=not recommended, 5=best)

| Chemical | Conditions | Result |
|-------------------------|------------|--------|
| Water | 15d, 80°C | 5 |
| Salt water (saturation) | 15d, 80°C | 5 |
| Xylene | 7d, 80°C | 2 |
| Ethyl acetate | 7d, 80°C | 1 |
| Isopropyl alcohol | 7d, 80°C | 0 |
| Sodium hydroxide (50%) | 7d, 80°C | 5 |
| Hydrogen peroxide (33%) | 7d, 25°C | 4 |
| Sulphuric acid (10%) | 7d, 80°C | 5 |
| Sulphuric acid (30%) | 30d, 80°C | 4 |
| Phosphoric acid (54%) | 7d, 80°C | 4 |
| Bleach | 7d, 80°C | 4 |
| Ammonia (3%) | 7d, 80°C | 5 |



KRYPTON CHEMICAL SL

C/ Martí i Franquès, 12 - Pol. Ind. les Tàpies
43890-l'Hospitalet de l'Infant- Spain
Tel: +34 977 822 245 - Fax: +34 977 823 977
www.kryptonchemical.com - rayston@kryptonchemical.com

Latest update:

21/2/2019

Page:

1/3



Pure polyurea membrane for waterproofing in spray applications.

| | | |
|------------------------------|-----------|---|
| Diesel | 16d, 80°C | 5 |
| Hydrochloric acid 12M (37%) | 7d, 80°C | 0 |
| Hydrochloric acid 6M (18%) | 7d, 80°C | 1 |
| Hydrochloric acid 3M (9%) | 7d, 80°C | 4 |
| Hydrochloric acid 0.75M (2%) | 7d, 80°C | 5 |
| Sodium hypochlorite 1% | 7d, 80°C | 3 |
| Engine oil | 21d, 80°C | 5 |
| Crude petroleum | 7d, 80°C | 5 |
| Sulfamic acid 85% | 21d, 23°C | 5 |
| Oleic acid | 7d, 80°C | 4 |
| Glycerine | 7d, 80°C | 0 |
| Ethanol/water 20/80 w/w | 7d, 80°C | 5 |
| | | 4 |

Adhesion strength

| Surface | Adhesion strength (MPa) |
|---|-----------------------------|
| Concrete (with epoxy primer) | 4.0 |
| Plywood (with epoxy primer) | 1.6 (cohesive wood failure) |
| Steel (PU primer) | 5.3 |
| High density PU foam (150kg/m3) | >1.5 foam failure |
| Fibrous cement (with Impermax LY as a primer) | 2.5 (cement failure) |

UV resistance

Polyurea Rayston is an aromatic isocyanate based product. A colour change is to be expected under sunlight. This change does not affect its mechanical properties. An additional UV protection can be provided with an Impertrans/Colodur topcoat.

Abrasion resistance

10 mg (Taber, 1000 c. CS-10, 1kg)

Tear strength

69 N/mm (ISO 34-1, method B)

Thermal resistance

Stable up to 200°C (6-hour test). According to low temperature tests, (UNE_EN 495-2001), the membrane can be folded at -45°C without cracking or breaks.

Fire resistance

B roof t1 (External fire exposure test). External fire exposure test (according to EN 13501-5:2005+A1 :2010)

Water permeability EN ISO 7783

0,9 g/m2 * d
Class II as per EN1504-2

Liquid water permeability EN 1062-3:2008

0,002 kg/m2 h0,5

Indentation

Polyurea Rayston gives, at 2-mm thickness, a resistance to indentation equivalent to a p4 level (approx 25 kg/cm2) at TH4 (90°C) as directed by EOTA guide ETAG 005.

The combined liner of Polyurea Rayston +selected geotextiles gives an static indentation resistance higher than 4000 kN (UNE-EN ISO 12236:2007)

SUPPORT REQUIREMENTS

In order to achieve a good penetration and bonding, support must be:

1. Flat and leveled
2. Compact and cohesive (pull off test must show a minimum resistance of 1,4 N/mm2).
3. Even and regular surface
4. Free from cracks and fissures. If any, they must be previously repaired.
5. Clean and dry, free of dust, loose particles, oils, organic residues or laitance

Support temperature must be between 10°C and 40°C. Support moisture must be less than 4% Higher humidities do not prevent correct polymerization but may make adhesion increasingly difficult to substrates.

TEMPERATURE AND HUMIDITY CONDITIONS

Air temperature should be between 10°C and 40°C. Relative air humidity should be less than 85%. Higher humidities do not prevent correct polymerization but

may make adhesion increasingly difficult to substrates because of condensation on surfaces.

SUPPORT PREPARATION

Concrete substrates must be prepared mechanically using high pressure sand or abrasion, in order to remove the surface and obtain an open pore. Substrates must be primed and levelled until a regular surface is obtained. Sharp irregularities are eliminated using an abrading disc machine.

Eliminate all dust and loose particles from the substrate by brushing or vacuum cleaning. If underlying moisture is suspected, it is recommended to apply 2 coats of epoxy (Rayston Epoxy primer). First one as such and the second one with quartz sand spreaded over.

MIXING

Both the component A side and the component B side should be preconditioned between 25 °C - 30°C before loading. Stir and homogenise separately both components using suitable mixing equipment before being loaded into the machine. Add the required Pigment Spray to the A-component and stir before loading. Recirculate both components while heating up to the required application temperatures.

APPLICATION AND RECOMMENDED QUANTITIES

Polyurea Rayston must be applied using 2-component hot spraying equipment. Recommended temperatures are:

- Component A: 68°C
- Component B: 70°C
- Hose: 67°C

Pressure must be adjusted to 140 bar.

During spraying, check coating thickness to ensure curing evolution is correct. Polyurea Rayston is applied at 1,5-2,0 kg/m2, obtaining a 1,5-2 mm thickness. Please contact Krypton Chemical for specific application details.

CURING TIME

Polyurea Rayston cures to touch after a few minutes after application.

Approximate hardness values are provided here as reference only (1 mm, polypropylene support, 25°C 50% RH)

| time | Hardness shore A |
|--------|------------------|
| 5 min | 28 |
| 10min | 40 |
| 20 min | 55 |
| 1 hr | 70 |
| 24 hrs | 80 |
| 4 days | 88 |

RECOATING

It is recommended to obtain the right thickness with a single application.

Where an epoxy primer has been previously applied, spray Polyurea Rayston Fast only after the primer is fully cured.

RETURN TO SERVICE

Under most conditions (25°C, 50% rh), the membrane is rain-resistant after 10 minutes.

TOOL CLEANING

In order to keep equipment in good conditions (spraying gun, gaskets), it is recommended not to use solvents. A cleaning fluid like Rayston Fluid can be used instead. Component B must be thoroughly removed and replaced with this fluid.


CLEANING AND MAINTENANCE

A maintenance work must be carried out regularly on the treated roofs according to the intended use.

This work includes the following tasks:

- Leaf removal
- Grass, dirt, moss and other vegetation removal
- Keeping storm water system in good working order.
- Ensure gratings are in place, in order to prevent gutter obstructions.
- Check proper condition of several structures (flashing, seams, retaining walls...)
- Verification of possible damages due to improper use.





Pure polyurea membrane for waterproofing in spray applications.

If aesthetic appearance of the roof is an important issue, it is essential to regularly clean the surface with water (some mild detergent may be added), according to the use.

It may be necessary to reapply decorative layers (Impertrans, Colodur) if they are worn out due to traffic, weather, corrosion, etc.

For stain removal, a surface treatment with Rayston solvent or isopropyl alcohol may be attempted. Strong acids are totally inadequate. Some solvents may damage the membrane. If this happens, the affected area has to be cut and repaired with a new Polyurea Rayston application.

FAQ

| Problem | Question | Answer | Solution |
|--|-------------------|---------------------------------|--|
| Does not cure or remains sticky | Ratio AB correct? | Different pressure | Check and correct pumping equipment |
| Bubbles or open holes in the membrane | Porous substrate? | No primer | Apply an Epoxy-type primer before Polyurea Open holes are frequent with fast-curing polyurea Use 1 kg/m2 minimum |
| Not enough hiding power | Horizontal? | Too few No pigment | Mix and homogenize pigment in component A before spraying |
| Gray colour darkens upon exposure to sun | Exposed? | Components react with UV light. | Apply an aliphatic topcoat afterwards (eg Impertrans, Colodur) |

SAFETY

Component B of Polyurea Rayston contains isocyanates and Component A contains corrosive polyamines that can cause burns. Always follow the safety instructions in the Material Safety Data Sheet. As a general rule, a good ventilation, protective clothing and respiratory protection is needed (combined organic vapor filters+particles A2P). This product must be used only for the applications here described. This product is intended for industrial and professional use. It is not suitable for DIY-type applications.

ENVIRONMENTAL PRECAUTIONS

Empty containers must be handled with the same precautions as if they were full. Treat empty containers as hazardous waste, and transfer them to an authorized waste manager. If the container still has some material left, do not mix with other product with no knowledge of potential dangerous reactions. Component A and B may be mixed on a 1/1 ratio in order to get an inert material, but never do it in volumes larger than 5 litres in order to prevent a dangerous heat evolution.

OTHER INFORMATION

The information contained in this DATA SHEET, as well as our advice, both written as verbal or provided through testing, are based on our experience, and they do not constitute any product guarantee for the installer, who must consider them as simple information.

We recommend to study deeply all information provided before proceeding to the use or application of any of our products, and strongly advise to conduct tests "on-site" in order to determine their convenience for a specific project.

Our recommendations do not exempt of the obligation of installers to deeply study the right application method for these systems before use, as well as to conduct as many preliminary tests as possible should any doubt arise. The application, use and processing of our products are beyond our control, and therefore under the exclusive responsibility of the installer. In consequence, the installer will be the only responsible of any damage derived from the partial or total in-observation of our indications, and in general, of the inappropriate use or application of these materials.

This data sheet supersedes previous versions.

