

Abrasion, Wear & Impact Protection Products- Chemical Resistance Chart

	201	202	203	204	205	206	209
Acetic acid >10%	2	2	2	3	2	2	3
Acetic acid 20%	4	4	4	4	3	3	4
Acetone	3	3	3	3	1	2	3
Ammonia Hydroxide 30%+	1	1	1	1	1	1	1
Benzene	1	2	2	2	1	1	2
Butanol	1	1	1	1	1	1	1
Carbonic acid 10-20%	1	1	1	1	1	1	1
Carbonic acid 20%+	2	2	2	2	1	1	3
Cyclohexane	1	1	1	1	1	1	1
Diesel	1	1	1	1	1	1	1
Diethanolamine	1	1	1	1	1	1	1
Ethanol	2	2	2	2	1	1	2
Formic acid 10%	3	3	3	3	2	2	4
Fuel Oil	1	1	1	1	1	1	1
Glycerine	1	1	1	1	1	1	1
Hydrochloric acid 10-20%	1	1	1	1	1	1	1
Hydrochloric acid 20-30%	2	2	2	2	2	1	1
Hydrochloric acid 36%	2	2	2	2	2	1	2
Hexane	1	1	1	1	1	1	1
Isopropanol	1	1	1	1	1	1	1
Lactic acid 20%	2	2	2	2	3	2	2
Naphtha	1	1	1	1	1	1	1
Nitric acid 10%	1	1	1	1	2	1	1
Nitric acid 10-20%	2	2	2	2	2	1	2
Nitric acid 20-30%	4	4	4	4	4	1	2
Phosphoric acid 30%	2	2	2	2	2	1	1
Phosphoric acid 50%	3	3	3	3	3	1	3
Sodium Hydroxide 30%	1	1	1	1	1	1	1
Sodium Hydroxide 50%	2	2	2	2	1	1	2
Sodium Hypochlorite 6%	2	2	2	2	2	2	1
Sodium Hypochlorite 15%	3	3	3	3	3	3	1
Sulphuric acid 10%	1	1	1	1	2	1	1
Sulphuric acid 10-20%	2	2	2	2	2	1	1
Sulphuric acid 50%	3	3	3	3	2	1	1
Sulphuric acid 98%	4	4	4	4	2	1	3
Toluene	3	3	3	3	1	2	2
White spirit	1	1	1	1	1	1	1

1: Suitable for immersion (20° C). 2: Suitable for short term immersion 72hrs (20° C). 3. Suitable for splash resistance 4. Unsuitable for contact