

PRODUCT DESCRIPTION

REPFLO 2042 HW is a two component solvent free epoxy metal repair compound containing ceramic beads to repair and protect equipment exposed to extreme wear environments from fine particles & wet slurries.

TYPICAL APPLICATIONS

Suitable for repairing and protecting surfaces suffering from severe erosion and fine particle wear such as:

- Slurry Pumps
- De watering pumps
- Bins and Hoppers
- Chutes
- Screw conveyors
- Pipe elbows
- Fan blades and housings
- Wear plates

SURFACE PREPARATION

STEEL SUBSTRATE

Steel substrates should be abrasive blasted to ISO 8501/4 Standard SA2.5 (SSPC SP10/ NACE 2) and a minimum blast profile of 75 microns using an angular abrasive. Remove all residual blast debris and the surfaces inspected. Profile checks should be taken and recorded. Once blast cleaned, the surface must be degreased and cleaned using MEK or similar type material. All surfaces must be repaired before rusting or oxidation occurs.

PLEASE NOTE: Salt contaminated surfaces must be pressure washed with fresh clean water and checked using a suitable chloride measurement gauge. This process must be repeated until all ingrained contaminants have been sweated out of the surface.

MIXING AND APPLICATION

PRECAUTIONS

Warm the Base component to 15-25°C (60-77°F) before mixing and do not apply when the ambient or substrate temperature is below 10°C (40°F) or less than 3°C (37°F) above the dew point

MIXING

Mixing can be either partial or full units. If mixing the full unit, then ensure as much as possible of both the base and activator is dispensed from the containers onto a clean

plastic mixing surface. Mix using the spatula provided until a uniform material free from any streakiness due to unmixed product, while also ensuring there is no unmixed material left on the spatula or the mixing surface.

For part mixing the mix ratio is 2:1 by volume. Using the spatula take 2 equal measures from the base unit onto a clean plastic mixing surface. Clean the spatula thoroughly and take one equal measure from the activator unit and place next to the base unit and mix as above.

From the commencement of mixing the material should be used within 30 minutes at 20°C (68°F).

APPLICATION

Using the spatula provided or the applicator tool, apply the mixed material to the blasted profile. Ensure the product is firmly pressed in to the surface to fully wet out the profile to a smooth finish. The material can be applied in a single application at the recommended wet film thickness of 3-6mm. On flat even surfaces the use of a large straight edge will aid in a smooth even finish.

COVERGAE RATES

1.5kg (3.3lb) of fully mixed product will give the following coverage rates –

0.219m² at 3mm 2.245ft² at 120mil
0.111m² at 6mm 1.193ft² at ¼"

5kg (11lb) of fully mixed product will give the following coverage rates –

0.73m² at 3mm 7.848ft² at 120mil
0.37m² at 6mm 3.978ft² at ¼"

Please note that the coverage rates quoted are theoretical and do not take into consideration the profile or condition of the surface being coated.

CURE TIMES

At 20°C (68°F) the applied materials should be allowed to harden for the times indicated below before being subjected to the conditions indicated. These times will be extended at lower temperatures and reduced at higher temperatures:

Usable life	30 minutes
Minimum overcoating time	4 hours
Maximum overcoating time	8 hours
Full Cure	4 days

TECHNICAL DATA SHEET: REPFLO 2042 HW

FOR OPTIMUM PERFORMANCE

After an initial curing period of at least 4 hours at 20°C (68°F), raising the cure temperature progressively to 60 - 100°C (140-212°F) for up to 8 hours will result in improved mechanical, thermal and chemical resistance properties

OVERCOATING TIMES

Minimum - the applied material can be over-coated as soon as it is touch dry.

Maximum - the over-coating time should not exceed 8 hours at 20°C (68°F).

Where the maximum over-coating time is exceeded, the material should be allowed to harden before being abraded or flash blasted to remove surface contamination.

UNIT SIZES

Product is available in the following pack sizes –

1.5KG (3.3lb)

5KG (11lb)

COLOURS

Mixed Material	Mid Grey
Base Component	Mid Grey
Activator Component	Black

STORAGE LIFE

The shelf life of the product is typically 5 years if unopened and stored in cool dry conditions (15-30°C/ 60-86°F). Once opened replace the lid firmly and store as above.

TECHNICAL DATA

Please see the REPFLO HW Product Specification Sheet for detailed technical and performance data.

HEALTH AND SAFETY

Please refer to the product safety data sheet for detailed information on handling, storage, shipping and disposal.

TECHNICAL SUPPORT

Zoom Corrosion Technology offer complete technical support and assistance, from discussing application requirements to training approved local contractors. For further information please contact a REPCO representative or your nearest REPCO authorised dealer.

Legal Notice: The data contained within this Technical Data Sheet is furnished for information only and is believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the customer to determine the products suitability for use. Zoom Corrosion Technology accepts no liability arising out of the use of this information or the product described herein.

Repcos products are manufactured for:
Zoom Corrosion Technology
Pembroke Lodge, 3 Pembroke Road, Ruislip,
HA4 8NQ, England, UK
Tel: +44 (0) 794 934 1074
Email: sales@zoomct.com
www.zoomct.com

Zoom
CORROSION TECHNOLOGY